



PURE FLOORING SOURCE

SPEC SHEET FOR ROLLED FLOORING

SHORE HARDNESS	ASTM D-2240	60 +/- 5
DENSITY	ASTM D-792	75 lbs. cu. ft.
ELONGATION	ASTM D-412	70%
REBOUND	ASTM D-3574 (5/16")	45-60 %
TENSILE	ASTM D-412	200 psi
TABER ABRASION	ASTM C-501	.45
FLAME SPREAD	ASTM E-84	125
SMOKE DEVELOPED	ASTM E-84	Passes 250
COMPRESSION SET	ASTM D-395B	12 % or less
OZONE EXPOSURE	ASTM D-1149-86	No adversities
AGING RESISTANCE	ASTM D-750	No change
TEAR STRENGTH	ASTM D-624	50 psi

Granulate: 1-3 mm EPDM
Binder: Urethane
Warranty: 1 Year by Manufacturer Materials only.

NOTE: Vius Flooring shall warranty the flooring materials it has supplied to be free from manufacturing defects for a period of 1 year from date of substantial completion and the flooring contractor shall warrant the installation to be free from defects for the same period. The foregoing warranty is in lieu of and excludes all other warranties not expressly set forth herein, whether express or implied, including, but not limited to any implied warranties of merchantability or fitness.

(Skive / Knife marks on product is an inherent characteristic of using re-cycled rubber and will not be viewed as an appropriate reason for rejecting the final finished product.)

Vius Flooring and its contractors shall not be liable for incidental or consequential losses, damages, or expenses, directly or indirectly arising from the sale, handling or use of the goods, or from any other cause relating thereto, and their liability hereunder in any case is expressly limited to the replacement of goods of complying with this agreement, or, at their election, to the repayment of, or crediting Buyer with, an amount equal to the purchase price of such goods, whether such claims are for breach of warranty negligence.



PURE FLOORING SOURCE

SPEC SHEET FOR ROLLED FLOORING (Cont)

ADHESIVE: Urethane base recommended
LINE PAINT: Suitable for interior or exterior synthetic rubber.
STORAGE: Rolls on side, minimum 55 degrees Fahrenheit,
less than 50 % humidity.

SUB-FLOORING: Should not vary more than 1/8" in ten ft.
NEW CONCRETE/ASPHALT: 30 days cure prior to installation of rubber.
MAINTENANCE: Under normal usage light mopping; common
detergents if needed.

STANDARD ROLL: 4ft WIDE BY PREDETERMINED

SHIPMENT: F.O.B. Factory

Physical properties can vary by product type; above information applies.

Every effort is made in the manufacture of the prefabricated matting for size, color and density consistency within a given lot #, slight variations can occur from lot # to lot #.



PURE FLOORING SOURCE

SPEC SHEET FOR TILED FLOORING

FORMULA

DENSITY 65# CUBIC FT
TENSILE (Machine Direction) 250 PSI
ELONGATION AT BREAK 100%
TEAR 70 PPI DIE C

106 COLOR FLECK

WIDTH = +/- 1/4 "
36" CUT AT 36.5 +/-
48" CUT AT 48.5 +/-
THICKNESS +/- .020
TILE 36X36 = +/- .078
THICKNESS = +/- .020

TYPICAL SPECIFICATIONS

SHORE HARDNESS	ASTM D-2240	60 +/- 5
DENSITY	ASTM D-792	65 lbs. cu. ft.
ELONGATION	ASTM D-412	100%
TENSILE	ASTM D-412	250 psi
TABER ABRASION	ASTM D-3884	0.47
FLAME SPREAD	ASTM E-84	135
SMOKE DENSITY	ASTM E-84	< 450
COMPRESSION SET	ASTM D-395	8.40%
VOC EMISSIONS	ASTM D-5116	.5 mg / m ² or less
RESISTANCE TO CHEMICALS	ASTM F925-02	No change
STATIC LOAD LIMIT	ASTM F970-00	-0.001 in.

CHEMICAL RESISTANCE

Ammonia - Good	Human Sweat - Good	Alkaline Base - Good
Bleach - Good	Alcohol - Good	Petroleum Oils - Good
Disinfectant - Good	Oxidizing Acids (concentrated) - Weak	

GRANULATE: Color - 1-3 mm EPDM ; Black - 8/16 SBR
BINDER: Urethane
WARRANTY: One Year by Manufacturer Materials. Liability is limited to replacement of product to original consumer.



PURE FLOORING SOURCE

SPEC SHEET FOR TILED FLOORING (Cont)

ADHESIVE:	Urethane base recommended
LINE PAINT:	Suitable for interior or exterior synthetic rubber
STORAGE:	Rolls on side, minimum 55 degrees Fahrenheit, less than 50% humidity
SUB-FLOORING:	Should not vary more than 1/8" in ten ft.
NEW CONCRETE/ASPHALT:	30 days cure prior to installation of rubber
MAINTENANCE:	Under normal usage light mopping; common detergents if needed

Physical properties can vary by product type; above information applies.

Every effort is made in the manufacture of the prefabricated matting for size, color and density consistency within a given lot #, slight variations can occur from lot # to lot #.

NOTE: with more than 1 Roll will be marked with a letter starting with "A" thru whatever letter corresponds with the number of rolls ordered. (Exp: If there are 3 rolls ordered then the rolls will be marked A, B, C.) This is to insure that the rolls are laid out correctly at the time of installation. "A" and "B" should be laid against each other, as should "B" against "C", so on and so forth. Improper installation could result in gaps in the seams of the material.

Note: Skive / Knife marks on product is an inherent characteristic of using re-cycled rubber and will not be viewed as an appropriate reason for rejecting the final finished product.