



IMPRESSIONS

Technical Information and Specifications

Test	Measure	Test Method
Wear Resistance	AC3	EN 13329: 2000
Level of Use	Approved for Commercial Classes 31	EN 13329: 2000
Impact Resistance	IC1	EN 13329: 2000
Static Resistance (mm)	No Visible Change $\leq$ 0.01 mm Indentation	EN 13329: 2000
Resistance to cigarette burns	Class 4 Exceeds Requirements (Best Value)	EN 13329: 2000
Resistance to staining	Class 5 Exceeds Requirements (Best Value)	EN 13329: 2000
Light Resistance	No Effect/Class 6 (Blue Wool) Class 4 (Gray Scale)	EN 13329: 2000
Thermal insulation including PE film and foam	$<0.10\text{m}^2\text{K/W}$	DIN 52612
Anti-Static resistance	2×10^{10} ohm	DIN 51953
Electric charge deviation	0.9kV	DIN 54345
Caster Chair	25,000 Cycles No Damage	EN 13329: 2000
Formaldehyde Emission	$<0.10\text{ppm}$	EN 717 ASTM 1333
Slip resistance	0.60 SCOF	ASTM C1028-89
Smoke Density – Flaming	226	ASTM E 662-95
Smoke Density – Non flaming	324	ASTM E 662-95
Critical Radiant Flux	Class 1 Exceeds Requirements (Best Value)	ASTM E 648-91

Product Specifications

Total Plank Thickness	7mm
Joint	Glueless Click
Core material	Premium high density fibreboard
Plank Dimensions	50.63" x 7.64" (1286mm x 194mm) 9 planks per carton (24.17 sq. ft.)
Warranty	20 years Limited Residential